

RT-108C

Mono-directional Filament Tape



Product Description

It is a heavy strength fiberglass reinforced biaxially-oriented polyester film tape with a aggressive solventless pressure sensitivesynthetic rubber and resin adhesive with clean removal feature. Exhibits steady strength excellent adhesion to bundling and strapping heavy duty, like bundling steeling coil, oil pipeline applications, etc.

Main Application

- * Unitizing
- * Bundling,
- * Electric
- * Strapping
- * Application where requires residue free, etc

Construction

*Backing:	Polyester film	*Adhesive:	Pressure sensitive synthetic rubber and resin
*Color:	Clear	*Reinforceme	Mono-directional continuous glass yarn

Typical Physical Properties

Note: The following technical information and data should be considered representative or typical only, and should not be used for specification purposes.

Typical Physical Properties

Total Thickness:	0.15 mm	5.9 mil	ASTM D-3652
Adhesion to Steel:	18.5 N/25mm	67 oz/ in	ASTM D-3330
Tensile strength:	1,450 N/25mm	326 lbs/in 59.18 kg/cm	ASTM D-3759
Elongation at Break:	3~5%		ASTM D-3759

Service Tem recommended: -10°C to 85°C

Storage Conditions

Store behind present stock. Store in a clean, dry place. Temperature of 4~26 °C (40~80 °F) and 40~50% relative humidity are recommended. Rotate your stock.

Navi Rudder Indu Co., Limited
Rudder(Xiamen) Industrial Co., Ltd.

#306, No 18 Huli Av, 361000,
Xiamen Area of China (Fujian) Pilot Free Trade Zone.
E: sales@ruddertape.com
Website: www.ruddertape.com

Rudder Tape prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommends are provided to the best of our knowledge on the basis of our practical experience. Nevertheless R.T can make no warranties, express or implied, including, but no limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the R.T products is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our staff will be glad to advise you.